



THE
ONE
AND
ONLY

100%
ECO



5180-10

Latex Interior Ceiling Flat Paint

Type	Acrylic
Gloss Level	Matte / 2% - 5% (60°)
Viscosity	95 – 100 K.U
Coverage	40 m ² (430 ft ²) / 3.78L 200 m ² (2150 ft ²) / 18.9L
Cleaner / Thinner	Water
Sizes	3.78 litres and 18.9 litres
Drying Time	Touch: 30-60 min. Recoat: 4 hours ¹
Concentration of Solids	By weight: 40% to 60%
VOC	40 g/L (average)

Colour

○ 5181 - 10 MOONLIGHT WHITE*

Description

The eco-friendly ceiling flat paint has been selected according to high standards in the paint industry. The hiding power is an asset in this type of application. In addition to reducing our carbon footprint, this paint will deliver the desired effect for an even and pleasant application. This paint can be used in most rooms of the house.

Colouring**

This product should not be tinted to preserve its properties. Colour may vary slightly from batch to batch. **Colours reproduced on paper may differ from actual paint colours.

WARNINGS: Keep out of reach of children. Keep this product from freezing.

¹Drying may take longer in cold, humid conditions.

Before using this product, consult its Material Safety Data Sheet for use of protective equipment (section 8), preventive measures (section 7), emergencies and first aid procedures (section 4). The above data is provided by Laurentide Paint for information purposes only and in no way constitutes a representation, promise or warranty as to the use, duration or quality of the product. The identified product must be used strictly in accordance with the specifications mentioned and any other instructions, warnings or directives issued by Laurentide Paint and its parent company Société Laurentide inc.

Storage

Store in a dry, well-ventilated place at room temperature (approx. 20°C). Avoid freezing.

Restrictions

Do not apply in extreme humidity, excessive heat or direct sunlight. Do not use this paint for bathrooms, floor or damp areas. Do not use on bare metal. Primer is required.

Surface Preparation

Surface preparation is vital to the ultimate success of the project. All surfaces must be clean, dry and free from all traces of contaminants (such as traces of soap) and mould. High gloss or rougher surfaces should be sanded to allow for better paint adhesion for a more uniform finish. Remove old, flaking paint. Thoroughly clean the surface to be painted with a solution of trisodium phosphate (TSP). Rinse well and allow to dry.

New gypsum or plaster: Apply a latex primer (5188-05).

Bare wood (resinous): According to wood type (pine, spruce, cedar) apply one coat of primer.²

Bare wood (non-resinous): Apply a latex primer or a first diluted coat (water, 10 to 15% by volume) for a better wood absorption. Then, apply two undiluted coats for a better result.

Consult your municipality for proper disposal of leftover product or the following link:
ecopeinture.ca



5180-10

Latex Interior Ceiling Flat Paint

Alkyd-painted surfaces: Apply a transition primer.²

Latex-painted surfaces: Apply this product as is.

Application

Shake the container well before use. Use a spatula to stir to the bottom of the container. Apply with a synthetic fibre brush (polyester, nylon) or a good quality anti-lint roller (10 mm). Never apply below 10°C or above 32°C. Humidity should be below 50%. Ventilate the room well. For best product efficiency, two coats should be applied. Applying one coat of paint over another that is not dry will extend the drying time. Allow sufficient drying time between coats. Drying time may vary according to temperature, humidity, ventilation and thickness of paint applied.

Application with a spray gun

Each application, such as a primer or topcoat, requires the combined choice of certain components such as the nozzle and application filters. Tools such as nozzles also need to be very clean to ensure flawless results. It is important to dilute the product by 5% to 8% with water to ensure even application.

- Recommended viscosity: Minimum of 75-80 KU
- Instructions for interrupting production: Thoroughly rinse or clean the nozzle and air cap and keep the paint containers closed to avoid skin formation.
- Cleaning product: Hot water if possible, otherwise water only. A cleaning solvent may be used if there is dry paint on the equipment.
- Drying time: Touch dry (2 hours) or through dry (4 hours).

Conventional spray gun

For uniform paint application, we generally recommend:

- Nozzle of minimum 1.8 to 2.0 mm, 40-45 PSI for supply.

Air-assisted spray gun

For uniform paint application, we generally recommend:

- Nozzle 0.013 to 0.017, gun pressure 1500 PSI to 2500 PSI.
- Kremlin nozzle: Minimum of 06xx.

Airless Pump Gun

For uniform paint application, we generally recommend:

- Nozzle 0.013 to 0.017, gun pressure 1500 PSI to 2500 PSI.
- Graco Nozzle: Model RAC X 213 to 617

Tool cleaning

Wash with soapy water.

Maintenance instructions

It is best to use a soft cloth or sponge and a mild household soap. Do not use abrasive or greasy cleaners. Rinse off any soap residue thoroughly. To ensure full efficiency of this paint, wait a minimum of 3 to 4 weeks for it to dry before washing the surface for the first time. cleaners. Rinse off soap residue thoroughly. To allow a full performance of this paint, wait a minimum of 3 to 4 weeks before washing or checking its adhesion.

You can visit our website at boomerangpaint.com or write to us at info.boomerang@laurentide.co

² For additional information or inquiries, do not hesitate to contact our client services department specialist.

Before using this product, consult its Material Safety Data Sheet for use of protective equipment (section 8), preventive measures (section 7), emergencies and first aid procedures (section 4). The above data is provided by Laurentide Paint for information purposes only and in no way constitutes a representation, promise or warranty as to the use, duration or quality of the product. The identified product must be used strictly in accordance with the specifications mentioned and any other instructions, warnings or directives issued by Laurentide Paint and its parent company Société Laurentide inc.

