



5188-05

Primer-Sealer and Undercoater – Interior

Type	Acrylic
Viscosity	95 – 100 KU.
Coverage	40 m ² (430 ft ²) / 3.78L 200 m ² (2 150 ft ²) / 18.9L
Cleaner/thinner	Water
Sizes	3.78 litres and 18.9 litres
Drying time	Touch: 30 to 60 minutes Recoat: 4 hours ¹
Concentration of solids	By weight : 40 to 60 %
VOC	43 g/L (average)
Color	5188-05 WHITE

Description

Eco-friendly interior acrylic primer-sealer and undercoater for new or painted surfaces. Can be used in any room of the house, for their walls and ceiling. A ceiling flat is also available in Moonlight White colour (5181-10). Easy to apply, excellent adherence, non-splattering and excellent hiding capacities.

Colouring

This product should not be tinted to preserve its properties. Colour may vary slightly from batch to batch.

Storage

Store in a dry, well-ventilated place at room temperature (approx. 20°C).
Avoid freezing.

WARNINGS: Keep out of reach of children.
Keep this product from freezing.

¹Drying may take longer in cold, humid conditions.

Before using this product, consult its Material Safety Data Sheet for use of protective equipment (section 8), preventive measures (section 7), emergencies and first aid procedures (section 4). The above data is provided by Laurentide Paint for information purposes only and in no way constitutes a representation, promise or warranty as to the use, duration or quality of the product. The identified product must be used strictly in accordance with the specifications mentioned and any other instructions, warnings or directives issued by Laurentide Paint and its parent company Société Laurentide inc.

Restrictions

Do not apply in extreme humidity, excessive heat or direct sunlight. This product is not recommended on resinous wood. Do not use this primer on the floor.

Surface preparation

Surface preparation is vital to the ultimate success of the project. All surfaces must be clean, dry and free from all traces of contaminants (such as traces of soap) and mould. High gloss or rougher surfaces should be sanded to allow for better paint adhesion for a more uniform finish. Remove old, flaking paint. Thoroughly clean the surface to be painted with a solution of trisodium phosphate (TSP). Rinse well and allow to dry.

New gypsum or plaster: Plaster must be clean and dry before painting. Make sure all dust has been removed after sanding.

Bared wood (resinous): According to wood type (pine, spruce, cedar...) apply anti-bleeding primer.²

Bared wood (non-resinous): Apply a first coat thinned 15%. Apply second coat as it is.

New concrete, cement: New concrete must be dry before being painted. It must dry at least one month per inch of thickness. Wash with muriatic acid and rinse thoroughly. Apply one coat as is.

Consult your municipality for proper disposal of leftover product or the following link:
ecopeinture.ca



5188-05

Primer-Sealer and Undercoater – Interior

Previously alkyd-painted surfaces: Apply as is.

Previously latex-painted surfaces: Sand to remove the finish and reduce shine in glossy areas. Remove dust. Apply product.

Application

Shake the container well before use. Use a spatula to stir to the bottom of the container. Apply with a synthetic fibre brush (polyester, nylon) or a good quality anti-lint roller (10 mm). Never apply below 10°C or above 32°C. Humidity should be below 50%. Ventilate the room well. For best product efficiency, one coat should be applied. Applying one coat of paint over another that is not dry will extend the drying time. Allow sufficient drying time between coats. Drying time may vary according to temperature, humidity, ventilation and thickness of paint applied.

Application with a spray gun

Each application, such as a primer or topcoat, requires the combined choice of certain components such as the nozzle and application filters. Tools such as nozzles also need to be very clean to ensure flawless results. It is important to dilute the product by 5% to 8% with water to ensure even application.

- Recommended viscosity: Minimum of 75-80 KU
- Instructions for interrupting production: Thoroughly rinse or clean the nozzle and air cap and keep the paint containers closed to avoid skin formation.
- Cleaning product: Hot water if possible, otherwise water only. A cleaning solvent may be used if there is dry paint on the equipment.

- Drying time: Touch dry (2 hours) or through dry (4 hours).

Conventional spray gun

For uniform paint application, we generally recommend:

- Nozzle of minimum 1.8 to 2.0 mm, 40-45 PSI for supply.

Air-assisted spray gun

For uniform paint application, we generally recommend:

- Nozzle 0.013 to 0.017, gun pressure 1500 PSI to 2500 PSI.
- Kremlin nozzle: Minimum of 06xx.

Airless Pump Gun

For uniform paint application, we generally recommend:

- Nozzle 0.013 to 0.017, gun pressure 1500 PSI to 2500 PSI.
- Graco Nozzle: Model RAC X 213 to 617

Tool cleaning

Wash with soapy water.

Maintenance instructions

It is best to use a soft cloth or sponge and a mild household soap. Do not use abrasive or greasy cleaners. Rinse off any soap residue thoroughly. To ensure full efficiency of this paint, wait a minimum of 3 to 4 weeks for it to dry before washing the surface for the first time.

You can visit our website at boomerangpaint.com or write to us at info.boomerang@laurentide.co

² For additional information or inquiries, do not hesitate to contact our client services department specialist.

Before using this product, consult its Material Safety Data Sheet for use of protective equipment (section 8), preventive measures (section 7), emergencies and first aid procedures (section 4). The above data is provided by Laurentide Paint for information purposes only and in no way constitutes a representation, promise or warranty as to the use, duration or quality of the product. The identified product must be used strictly in accordance with the specifications mentioned and any other instructions, warnings or directives issued by Laurentide Paint and its parent company Société Laurentide inc.

